


Unique D-5 Free Silicone Elastomer

What is Silicone Elastomer?

Due to three-dimensional structure, Silicone Elastomer has good thixotropic effect and elastic softness (silky and matt touch) for additive of cosmetic products.

Swollen Silicone Elastomer Particle



Product Name	Composition/INCI Names		Refractive Index	Viscosity (cPs)	Coutertype
SANSIL-D308	Dimethicone (3cst)	92%	1.390 ~ 1.405	30,000 ~ 100,000	-
	Dimethicone/Vinyl Dimethicone Crosspolymer	8%			
SANSIL-200S	Dimethicone (6cst)	75%	1.395 ~ 1.415	70,000 ~ 200,000	KSANSIL-16
	Dimethicone/Vinyl Dimethicone Crosspolymer	25%			
SANSIL-5041	Dimethicone (5cst)	80%	1.390 ~ 1.405	100,000 ~ 300,000	DC 9041
	Dimethicone Crosspolymer	20%			
SANSIL-260	Dimethicone (6cst)	80%	1.395 ~ 1.415	100,000 ~ 400,000	DMG-6
	Dimethicone/Vinyl Dimethicone Crosspolymer	20%			
SANSIL-650DF	Dimethicone (5cst)	50%	1.390~ 1.405	10,000 ~ 60,000	-
	Isododecane	40%			
	Stearyl Dimethicone	2%			
	Dimethicone/Vinyl Dimethicone Crosspolymer	8%			
SANSIL-600DF	Dimethicone (5cst)	36%	1.390~ 1.405	50,000 ~ 100,000	-
	Isododecane	40%			
	Stearyl Dimethicone	10%			
	Dimethicone/Vinyl Dimethicone Crosspolymer	14%			
SANSIL-7001	Dimethicone/Vinyl Dimethicone Crosspolymer	8%	-	20,000 ~60,000	-
	Dimethicone (3cst)	64%			
	Water	25%			
	Butylene glycol	2%			
	Polyglutamic acid	1%			

Fluoro Silicone Oil

FLUORO SILICONE COMPOUNDS

Inclusion of fluoro groups into silicone backbone results in lowering of surface tension, increased spreadability and solubility when compared to the non-fluoro dimethicone of the same molecular weight.


APPLICATIONS

SKIN CARE

- Skin protectants
- Detackifiers for creams and lotions
- Water-repellents
- Skin feel modifiers
- Additives to reduce emulsion soaping
- Long-lasting effect

MAKE-UP

- Lip Gloss
- Lipsticks
- Pigment dispersant
- Mascara



Grade	INCI name	Appearance	Viscosity(cps)	Refractive Index
SF-30	Perfluorononyl ethyl Stearyl Dimethicone	Colorless	200 ~ 1,000(25°C)	1.400 ~ 1.423
SF-30W	Perfluorononyl ethyl Stearyl Dimethicone	Translucent Wax or paste	400 ~ 1,000(40°C)	1.400 ~ 1.423
BSFL-30	Trifluoropropyl Dimethicone	Colorless	~ 400(25°C)	1.370 ~ 1.390



DISTRIBUTED BY

UNIT 2 CORNUM INDUSTRIAL ESTATE
RAANS ROAD, AMERSHAM
HP8 5JQ, UNITED KINGDOM
TEL: +44 (0) 1494 40160
FAX: +44 (0) 1494 72220
EMAIL: SALES@AMMEREX.COM

Sandream Enterprises, LLC, 373 Rt. 46 W, Building E, Fairfield, NJ 07004, USA
Tel: +1 973-882-3077 Fax: +1 973-882-3088 Email: sandream@sandreamllc.com